

CC1510

Acid Catalysing Clear GLOSS Non-Yellowing

DESCRIPTION & USES Two-component acid catalysed (amino-alkyd) clear gloss designed for the wetting treatment of most light coloured timbers. Based on non-yellowing binders, this lacquer has excellent resistance to yellowing or yellowing caused by heat and provides a tough, durable and flexible surface. This high build multi-coat clear has good drying and sanding properties and can be used to both seal and topcoat. For protection against colour change of the timber substrate caused by UV/sun light a UV prohibitor* can be added to CC1510 before application (*refer TD sheet on XT170-AC*).

Recommended Application:

For use as a non-yellowing high gloss finish on furniture, joinery, shop-fitting, wardrobe & kitchen doors, commercial interiors.
N.B Not recommended for use in wet areas (i.e kitchen benchtops, vanity tops etc)

DRY FILM PROPERTIES

Colour: Clear
Gloss: 80% Gloss

WET PROPERTIES

Solid content: 40 ±1 (%)
Specific gravity: 922 ±30 (Kg/M²)
Viscosity in drum: 70-80 seconds DIN Cup 4 @ 20°C
Shelf life: 12 months in sealed containers

APPLICATION

Method: Spraying conventional
Mixing Ratio: 10 parts CC1510 to 1 part DV311 hardener
Thinning: DT8900 or BECKER22 or THIN2221 at 20-35%
(Depending on type of equipment used)
In hot/humid/rainy conditions NT573 can be added
Pot Life: 1-2 days (approx)
Drying: 4-6 hours at 20°C or 30-40 minutes at 70°C

NOTES

Do not use over FF810 sealer
We recommend using a polyurethane sealer when coating Beech and Tasmanian Blackwood
All kind of drying requires good ventilation and circulation.
Do not stack before surface temperature is below 30°C
Contact us for further information

FOR INDUSTRIAL USE ONLY Data shown are mean values and cannot be construed as product specifications. Users are advised to make their own tests to determine the suitability of products for their own purposes.

AUSTRALIAN DISTRIBUTORS FOR SHERWIN WILLIAMS

WA: TWENTY TWO SERVICES P/L **Tel** (08) 9206 0220 **Fax** (08) 9206 0974
NSW: CROMA COATINGS **Tel** (02) 9533 9122 **Fax** (02) 9533 9299
VIC: CROMA COATINGS VICTORIA **Tel** (03) 9768 2312 **Fax** (03) 9768 2389
QLD: CROMA COATINGS QUEENSLAND **Tel** (07) 3386 1000 **Fax** (07) 3386 1003

Email info@22croma.com.au
Web www.22croma.com.au